



High Performance Floor
Coatings and
Re-Surfacing Screens

EPOXY SEALERS



DRYFIX EPOXY SEALER

- **Solvent Free**
- **Virtually Odourless**
- **Seal and dust proof concrete**
- **Excellent Chemical Resistance**
- **Rapid curing — Early Return to Use**



EPOXY SEALER is a two-part, solvent free, epoxy resin for sealing and impregnating concrete floors that demand outstanding performance. A tough, durable, chemical resistant surface that are easy to clean. The glazed finish is capable of withstanding heavy fork trucks and intense pedestrian trafficking.

USES: This sealer is most suitable for application to garages, factory floors, warehouses, workshops, food processing areas and storerooms, warehouses and most concrete floors that demand a tough, dust free environment, can withstand fork trucks and offer high chemical spillage resistance.

PREPARATION: Concrete floor surfaces must be clean, sound, dry and free from grease, oil and other forms of contamination. Concrete laitance should be removed by either acid washing using Concrete Etch or by floor grinding. For large areas, light Vacuum Track Shot Blasting is recommended. This sealer must not be applied onto previously painted floors. New concrete should be at least 14 days old.

MIXING APPLICATION: Empty the entire contents of Pack "B" (Hardener) into Pack "A" (Resin) and stir using a mixing paddle and an electric drill on a slow speed for 3 minutes. For small quantities mix by hand. Ensure you reach both the sides and bottom of the container during the mixing process. Once fully mixed use all within 35 minutes.

APPLICATION: Apply the sealer immediately after mixing by brush or roller. Two coats are normally required for maximum resistance. For best inter coat adhesion, apply the second application immediately the first coat is touch dry normally the following day. Anti-slip aggregates can be scattered upon the sealer while still tacky, to provide some slip resistance for wet areas.

HEALTH AND SAFETY: Read the Health and Safety Data Sheet prior to handling.

Alliance Remedial Supplies Limited

Unit 11-12 Regent Trade Park, Gosport, Hampshire, PO13 0EQ

Tel: 01329 235252, Email: sales@arsstore.co.uk, Web: allianceremedialsupplies.co.uk

VAT: 119 914 303, Co Reg: 07814823



High Performance Floor
Coatings and
Re-Surfacing Screens

EPOXY SEALERS



PRODUCT DATA

COVERAGE: 4.5 Litres will cover up to 30M2 depending upon the site conditions that prevail i.e., porosity and texture and temperature of the substrate.

POT LIFE: When fully mixed, approximately 30 minutes @ 20°C. Extended pot life at lower temperatures, reduced at high temperatures.

CURING /HARDENING TIME: Tack free in 12 hours @ 20°C. Light traffic after 24 hours @ 20°C. Heavy traffic after 2 days. Full cure in 7 days @ 20°C. *DO NOT USE* at temperatures below 5°C.

CHEMICAL RESISTANCE: Resistant to spillages of many chemicals commonly met within industry.

PROPERTIES			
Parameter	Unit	Figure	Method
Hardness	Shore D	13°C, 24 hours	58
		23°C, 24 hours	69
		23°C, 7 Days	77
Compressive Strength	N/mm2	91.72	EN ISO 604
Bending Tensile Strength	N/mm2	72	EN ISO 178
Tensile Strength	N/mm2	41	EN ISO 527-1
Abrasion Resistance	mg	55	Taber abrasion

SLIP RESISTANCE: The fully cured product offers low slip resisting properties. For high slip resistance use Epoxy Safety Sealer. This product conforms to BS 7976-2 for Slip Resistance.

SHELF LIFE: 12 months in sealed containers. Protect from frost.

Whilst Alliance Remedial Supplies Limited endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it can not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification or information given.

Alliance Remedial Supplies Limited

Unit 11-12 Regent Trade Park, Gosport, Hampshire, PO13 0EQ

Tel: 01329 235252, Email: sales@arsstore.co.uk, Web: allianceremedialsupplies.co.uk

VAT: 119 914 303, Co Reg: 07814823