



High Performance Floor
Coatings and
Re-Surfacing Screens

EPOXY WATERPROOFING



DRYFIX EPOXY LIQUID SURFACE MEMBRANE

- **Liquid Applied Surface Membrane**
- **Apply to Dry and Damp Surfaces**
- **Solvent Free and Low Odour**
- **Oil Tolerant**



LIQUID SURFACE MEMBRANE is a twin pack, epoxy resin liquid surface membrane for concrete floors prior to the installation of vinyl sheeting, tiles, suspended timber floors, laminates, carpets and most resin flooring systems. This product will provide a barrier preventing residual moisture movement under hydrostatic pressure and an highly effective barrier to oil and other contaminants.

USES: It will provide protection against residual moisture or oil from affecting subsequent floor covering installations. Concrete surfaces can be dry or damp during the application. It is an ideal waterproofing coating for floors and walls in cellars, basements, plant rooms, inspection pits and water retaining structures.

PREPARATION: Ensure the surfaces are free from deep holes and wide cracks. Fill deep holes with PATCHING MORTAR or for small holes and cracks with Epoxy Filler For extremely uneven concrete, resurface using a water resistant, polymer modified, cement levelling topping prior to applying liquid surface membrane. To maximise performance - or as an unprotected wearing finish- all concrete to be treated must be sound, and as clean as possible. Remove all surface dust, grease oil and other contaminants. For small areas use of our 'Degreaser' (available to purchase from our web site) or for large areas vacuum shot blasting is recommended. Vacuum the areas prior to application.

Alliance Remedial Supplies Limited

Unit 11-12 Regent Trade Park, Gosport, Hampshire, PO13 0EQ

Tel: 01329 235252, Email: sales@arsstore.co.uk, Web: allianceremedialsupplies.co.uk

VAT: 119 914 303, Co Reg: 07814823



High Performance Floor
Coatings and
Re-Surfacing Screens

EPOXY WATERPROOFING



MIXING: Empty the entire contents of Pack “B” (Hardener) into Pack “A” (Resin) and stir using a mixing paddle in an electric drill on a slow speed for 3 minutes. Ensure you reach both the sides and bottom of the container during the mixing process.

APPLICATION: Apply one coat on smooth surfaces and two coats on textured Surfaces or when maximum performance is required. Apply the coating by roller immediately after mixing and use all within 30 minutes. When applying onto damp concrete ensure you work the coating well onto the surface. For damp proofing, where possible continue the membrane up the walls to meet the damp proof membrane. Do not cover expansion or construction joints.

COVERAGE: 4.5 Litre pack will cover around 20m² depending upon the porosity and texture of the substrate.

POT LIFE: When fully mixed, approximately 40 minutes @ 20°C

CURING /HARDENING TIME: Tack free after 10 hours @ 20° C. Apply second coat within 48 hours of first coat. Do not apply at temperatures below 5°C. After 24 hours at 20°C the surface is suitable for subsequent pressure adhesive or application of a subsequent resin flooring system.

SOLID CONTENT: 100%

CHEMICAL RESISTANCE: Good resistance to spillages of many chemicals commonly met within industry.

POT SIZES: 10kg & 20kg - Combined weight of Resin, Hardener and Filler.

COLOURS: Available in a range of colours.

Whilst Alliance Remedial Supplies Limited endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it can not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification or information given.

Alliance Remedial Supplies Limited

Unit 11-12 Regent Trade Park, Gosport, Hampshire, PO13 0EQ

Tel: 01329 235252, Email: sales@arsstore.co.uk, Web: allianceremedialsupplies.co.uk

VAT: 119 914 303, Co Reg: 07814823



High Performance Floor
Coatings and
Re-Surfacing Screens

EPOXY WATERPROOFING



PROPERTIES			
PARAMETER	UNIT	FIGURE	METHOD
Hardness 13°C 24 Hours	Shore D	22	DIN 53505
23°C 24 Hours		56	
23°C 7 Days		75	
Compressive Strength	N/mm ²	78	EN ISO 604
Bending Tensile Strength	N/mm ²	70	EN ISO 178
Tensile Strength	N/mm ²	41	EN ISO 527-1
Adhesion/Pull Off Strength	N/mm ²	2	DIN EN 13 578
Bond Strength	Far exceeds the cohesive strength of concrete.		
Abrasion Strength	Mg	55	Taber (CS10, 1000,1000)
Water Vapour Permeability	>3gms/m ² /day		

Whilst Alliance Remedial Supplies Limited endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it can not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification or information given.

Alliance Remedial Supplies Limited

Unit 11-12 Regent Trade Park, Gosport, Hampshire, PO13 0EQ

Tel: 01329 235252, Email: sales@arsstore.co.uk, Web: allianceremedialsupplies.co.uk

VAT: 119 914 303, Co Reg: 07814823